

TEST REPORT

NO.: A001R140610082004

Date: Jun 13, 2014

Page 1 of 6

Applicant: SHENZHEN FUXIANG TECHNOLOGY CO.,LTD

客户/申请商: 深圳市富翔科技有限公司

Address: NO.11 Building,Pioneer IndustryZone,Shapuwei,Songgang Town,Shenzhen

地 址: 深圳市宝安区松岗镇沙浦围创业工业区 11 栋

Report on the submitted sample said to be

委托测试的样品及申请者对样品的说明如下

Sample name: PCB circuit board

样品名称: PCB 线路板

Model: /

型 号: /

Material: OSP

材 料: OSP

Supplier: /

供 应 商: /

Sample received date: Jun 10, 2014

样品接收日期: 2014-06-10

Testing period: From Jun 10, 2014 to Jun 13, 2014

样品测试周期: 2014-06-10 至 2014-06-13

Test Requested 测试要求:

As specified by client, to determine the Lead(Pb), Cadmium(Cd), Mercury(Hg), Hexavalent Chromium(Cr⁶⁺), Polybrominated Biphenyls(PBBs) & Polybrominated Diphenyl Ethers(PBDEs) content in the submitted sample.

依据客户要求,测定委托样品中的铅(Pb)、镉(Cd)、汞(Hg)、六价铬(Cr⁶⁺)、多溴联苯(PBBs)和多溴联苯醚(PBDEs)的含量。

*****FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) 更多详细信息请查阅下页*****

Signed for and on behalf of 谨代表

Shenzhen AOV Testing Technology Co., Ltd. 深圳市安姆特检测技术有限公司



Tested by:

Leif

主 检 Li Xian Yong, Leif 李先勇

Project Leader 项目负责人

Reviewed by:

Rosary

主 审 Luo Jun, Rosary 罗君

Vice Technical Supervisor 技术副主管

Approved by:

Lewis

签 发 Liu Lin Wen, Lewis 刘林文

Technical Supervisor 技术主管

SHENZHEN AOV TESTING TECHNOLOGY CO., LTD

1F East,2-6F, Block 5,Yuantou Lane,Tanglang,Taoyuan Street, Nanshan District,Shenzhen,Guangdong,China

Tel: +86-755-8600 8000 Fax: +86-755-8600 8282 Http://www.aovt.com Postcode: 518055

(Attention is drawn to the terms and conditions printed overleaf)

Hotline
400 700 8600

TEST REPORT

NO.: A001R140610082004

Date: Jun 13, 2014

Page 2 of 6

Test Method:

测试方法:

(1) With reference to IEC 62321:2008 Ed 1.0 Electrotechnical products - Determination of levels of six regulated substances

参照 IEC 62321:2008 Ed 1.0 电子电气产品中六种限用物质含量的测定程序

(2) With reference to IEC 62321:2013 Ed 1.0 Determination of certain substances in electrotechnical products


参照 IEC 62321:2013 Ed 1.0 电子电气产品中某些物质含量的测定程序

Test Item 测试项目	Pretreatment Method 前处理方法	Measuring Instrument 测试仪器	MDL
Lead 铅	IEC 62321-5:2013 Ed 1.0 Section 7.3 IEC 62321-5:2013 Ed 1.0 7.3 部分	ICP-OES	2 mg/kg
Cadmium 镉	IEC 62321-5:2013 Ed 1.0 Section 7.3 IEC 62321-5:2013 Ed 1.0 7.3 部分	ICP-OES	2 mg/kg
Mercury 汞	IEC 62321-4:2013 Ed 1.0 Section 7.2 IEC 62321-4:2013 Ed 1.0 7.2 部分	ICP-OES	2 mg/kg
Hexavalent Chromium 六价铬	IEC 62321:2008 Ed 1.0 Annex C IEC 62321:2008 Ed 1.0, 附件 C	UV-VIS	2 mg/kg
Polybrominated Biphenyls/ Polybrominated Diphenyl Ethers 多溴联苯及多溴联苯醚	IEC 62321:2008 Ed 1.0 Annex A IEC 62321:2008 Ed 1.0, 附件 A	GC-MS	5 mg/kg

Test Flow:

测试流程:

1. To Determine Lead, Cadmium Content (测定铅, 镉含量):




TEST REPORT

NO.: A001R140610082004


Date: Jun 13, 2014

Page 3 of 6

2. To Determine Mercury Content (测定汞含量):



3. To Determine Hexavalent Chromium Content (for Electronics) (测定六价铬含量) (电子件):



TEST REPORT


NO.: A001R140610082004

Date: Jun 13, 2014

Page 4 of 6

4. To Determine Polybrominated Biphenyls/Polybrominated Diphenyl Ethers Content

(测定多溴联苯及多溴联苯醚的含量):



Test Results:

测试结果:

Item 项目	Unit 单位	Result (结果)
		A*
Lead 铅	mg/kg	3
Cadmium 镉	mg/kg	N.D.
Mercury 汞	mg/kg	N.D.
Hexavalent Chromium 六价铬	mg/kg	N.D.

TEST REPORT

NO.: A001R140610082004

Date: Jun 13, 2014

Page 5 of 6

Item 项目	Unit 单位	Result (结果)
		A*
多溴联苯 PBBs	mg/kg	N.D.
一溴联苯 MonoBB	mg/kg	N.D.
二溴联苯 DiBB	mg/kg	N.D.
三溴联苯 TriBB	mg/kg	N.D.
四溴联苯 TetraBB	mg/kg	N.D.
五溴联苯 PentaBB	mg/kg	N.D.
六溴联苯 HexaBB	mg/kg	N.D.
七溴联苯 HeptaBB	mg/kg	N.D.
八溴联苯 OctaBB	mg/kg	N.D.
九溴联苯 NonaBB	mg/kg	N.D.
十溴联苯 DecaBB	mg/kg	N.D.
多溴联苯醚 PBDEs	mg/kg	N.D.
一溴联苯醚 MonoBDE	mg/kg	N.D.
二溴联苯醚 DiBDE	mg/kg	N.D.
三溴联苯醚 TriBDE	mg/kg	N.D.
四溴联苯醚 TetraBDE	mg/kg	N.D.
五溴联苯醚 PentaBDE	mg/kg	N.D.
六溴联苯醚 HexaBDE	mg/kg	N.D.
七溴联苯醚 HeptaBDE	mg/kg	N.D.
八溴联苯醚 OctaBDE	mg/kg	N.D.
九溴联苯醚 NonaBDE	mg/kg	N.D.
十溴联苯醚 DecaBDE	mg/kg	N.D.

Specimen Description:

样品描述:

A*: PCB circuit board mixed PCB 线路板混测

Note:

备注:

- Specimens, which requested to determine Cadmium, Mercury and Lead Content, have been dissolved completely.
- 对于测试铅、镉、汞的样品已完全溶解
- mg/kg=ppm
- N.D.=not detected(<MDL)
- N.D.= 未检出(<MDL)
- MDL=Method Detection Limit
- MDL=方法检测限

TEST REPORT

NO.: A001R140610082004


Date: Jun 13, 2014

Page 6 of 6

- *According to the applicant's request, the admixture of specimen A is tested as a whole. The testing results of specimen A may be different from that of any sole material in specimen A.
- *根据客户的要求，对样品 A 进行混测。样品 A 的测试结果可能与单测样品 A 中任何一种材料的结果有差异。
- Photo is included
- 附照片

Photograph of Sample

样品照片



PCB circuit board

PCB 线路板

End of Report

报告结束